



INSTALLATION FOR MAKING A NONWOVEN TEXTILE WEB AND METHOD
FOR USING SUCH AN INSTALLATION

Background of the Invention and Related Art
Technical field

5 The present invention relates to an improved installation for making a nonwoven textile web, which is commonly referred to by the generic name of spunbond and which is formed by continuous synthetic filaments. *The invention also relates to*

10 ~~It also concerns~~ a method for using such an installation.

the following steps.

Prior art

The production of nonwoven webs of the spunbond type *is known in the art and*
15 ~~goes back decades and consists, generally speaking, includes~~

- ~~a) in~~ Extruding a melted organic polymer through a spinneret perforated with holes, so as to form a bundle or curtain of filaments,
- 20 *using* ~~b) then, in~~ Orienting the extruded filaments by drawing ~~by means of one or more fluid-jet~~ *is* particular compressed-air devices,
- ~~c) and finally, in~~ Receiving the bundle of filaments in the form of a web on a movable transporting belt, which is generally subjected to a suction source and the speed of which is adjusted according to the characteristics of the web, in particular weight per unit area, which it is desired to achieve.

25
30 After production, the web is consolidated, for example by performing a sizing or calendering. *is used* Preferably hot calendering, so that the elementary filaments are joined to one another.

35 Other consolidation treatments may also be performed, *may be used* such as for example, a needling treatment (conventional or by fluid jets), and/or the application of a bonding substance on the surface or in the interior of the web.

may be applied

A great number of proposals have been made for producing such webs, all having the aim of obtaining a web or sheet as homogeneous as possible with a high productivity and, increasingly, with elementary filaments of great fineness having a count less than 2 dtex, if possible.

Among the oldest documents for producing such webs, mention may be made of the patent GB-A-932 482, in which the filaments, after extrusion, move along in the open air on leaving the spinneret over a sufficient distance to permit at least surface solidification of the ~~extruded~~ ^{the} extruded filaments before they are introduced into a suction and drawing nozzle creating the formation of a high-speed annular air current.

~~In order to~~ ^{To bring about the} break-up of the bundle of filaments, the latter receive an electrostatic charge which may be obtained from an electrostatic generator causing a corona-type effect ~~located~~ upstream and downstream of the suction nozzle. *This causes*

Among the various parameters which must be taken into account for the production of good-quality webs, it is necessary, depending on the extruded polymers, to adapt the distance between the outlet of the spinneret and the inlet into the drawing system, the air speed inside the nozzle and also the exit speed of the filaments from the latter, so that the deposition on the receiving belt is regular.

^{the} To solve ~~this~~ problem of the homogeneity of the deposition on the conveyor belt, it has been proposed in the patent US-3,286,896 to design the suction device in the form of a narrow chamber of rectangular cross-section and of great length. ^{includes} Such an assembly comprising at the inlet a suction chamber for the extruded filaments, followed by an additional chamber where low-pressure air is

injected and a channel of great length, ^{wherein} ~~inside which~~ the high-speed air flows. In order to obtain a good distribution of the filaments over the receiving surface, a deflecting assembly which slows down the air flow is arranged at the outlet of the drawing chamber, ~~thus to permit~~ ^{to permit} ~~permitting~~ a better distribution of the filaments.

Such systems in which the filaments pass inside a suction and drawing chamber of rectangular shape, which may, where appropriate, have the width of the web of extruded filaments, have been proposed, ~~as emerges in particular from the~~ ^{and corresponds} French patent 2,064,087, ~~(corresponding to US 3,802,817)~~. The curtain of filaments ~~being~~ is subjected on both of its sides to the action of high-speed air streams causing the filaments to be drawn.

Furthermore, ^{also} ~~the~~ patent US 4,064,605 describes an improvement to such a technique which consists in providing an additional assembly for cooling the filaments, ^{includes} before introduction into the actual drawing chamber, ~~by subjecting the bundle of filaments to a transverse air current,~~

^{provision} Finally, the development of the technique has led to the production of installations in which the drawing of the filaments at the spinneret outlet and their transfer to a receiving belt are achieved without the filaments ever going into the open air at the spinneret outlet, ^{This is achieved by} ~~by virtue of~~ an integrated assembly making it possible to achieve the cooling, drawing and deposition of the filaments on the belt, ^{disclosed} ~~as emerges in particular from the~~ ^{US} patent US 4,627,811 and also ~~US~~ 5,814,349.

Such an installation design makes it possible to obtain nonwoven sheets with a low weight per unit area and good regularity, but it is complex and difficult to use.

Moreover, such installations lack versatility ^{due} ~~owing~~ to the fact that it is not possible to readily adjust the cooling conditions at the spinneret outlet, ^{such conditions} ~~which~~ vary according to the polymers and the filament count which it is desired to produce, and the final characteristics of the web.

In addition, such installations are ill-suited to the production of filaments of great fineness.

10

a spunbond nonwoven

Consequently, to date, no satisfactory solution has been proposed for designing an installation for producing nonwovens of the spunbond type with which it is possible to achieve a high productivity when the filaments are fine, that is, ~~to say~~ having a count less than 2 dtex, which means having a perfect and extremely regular drawing of the filaments without breakage thereof during this drawing phase.

20

Now, to achieve a high productivity, that is to say a high polymer delivery at the spinneret outlet, this means on the one hand that increasing the drawing speed in the drawing slot, thus entailing a high air flow rate coupled with a relatively high temperature of the filaments before drawing in order to preserve a certain plasticity thereof.

Furthermore, ~~X~~ drawing of the filaments coupled with a high productivity also means being able to brake the air streams at the outlet of the drawing slot to achieve a regular deposition of the filaments on the receiving conveyor and the production of a high-quality sheet.

30

In accordance with

Summary of the Invention

is provided

~~Now, there has been found, and this forms the subject~~
 of the invention, a novel type of installation for producing nonwoven textile webs from continuous synthetic

35

filaments, with which all the above-mentioned problems can be solved.

Generally speaking, the installation according to the invention is of the type comprising, in a conventional manner, *the following*:

- * At least one extruder for a melted organic polymer ^{to feeding} a spinneret for producing a curtain of filaments;
- * A cooling zone for bringing about at least surface solidification of the ^{the} said extruded filaments;
- * A suction device in the form of a narrow chamber of rectangular cross-section, inside which the curtain of filaments is subjected to the action of high-speed air streams causing the filaments to be drawn;
- * *An arrangement* means for deflecting and slowing down the air flow at the outlet of the drawing slot and for distributing the filaments homogeneously over a receiving belt.

The installation according to the invention *is characterised* in that the *means* for carrying out the different operational phases, namely extruding, *means*, cooling, *means*, filament-drawing assembly and distributing, *means*, are separate from one another and can be independently adjusted, *not only according to the production to be achieved (nature of the polymers, elementary count of the filaments produced, weight per unit area of the web produced), but also during the start-up phase of the production.*

By virtue of such a design, which *is contrary to* ~~goes against~~ the technical development in this field, directed towards producing completely integrated assemblies for the cooling, drawing and distribution of the filaments over the conveyor

6

Such advantages particularly include
belt, it was found that such a separation of the different
operational phases from one another afforded a very great
number of advantages, in particular, as regards the
flexibility of use and the possibility of adjusting the
5 production much more easily according to the yarn counts
and the web weight which it is desired to achieve.

Advantageously and in practice, according to the
invention:

- 10 * the cooling zone at the spinneret outlet and the
filament-drawing zone ~~consist of~~ ^{include} a plurality of
elementary modules placed side by side according
to the production width. The filament-opening
system consisting, for its part, ^{includes} of an assembly
15 extending over the entire width of the web
produced,
- * The cooling at the spinneret outlet is brought
about by ~~means of~~ an assembly having a plurality
of successive zones for subjecting the curtain of
20 ^{the air} filaments to a transverse air current. The speed
^{current} and temperature of ~~which~~ may be adjusted
independently in each of the zones,
- * The filament-drawing device ^{includes} ~~has~~ a suction slot ^{having a}
the width of which may be adjusted automatically
25 according to the production of the machine,
- * The filament-opening system, which is spaced from
the outlet of the drawing system, ^{includes} ~~consists of~~ an
assembly which laterally deflects the air flow ^{to}
30 ^{of the filaments} ~~reducing~~ the speed thereof and that of the
filaments, ^{This facilitates} ~~and facilitating~~ the uniform
deposition on the conveyor by eliminating any
rebound at the moment of this deposition.
Advantageously, the filament-opening system is
35 also associated with an assembly which
electrostatically charges the ~~said~~ filaments
before deposition on the receiving belt and which
may be arranged either immediately at the outlet

of the ~~said~~ opening system or integrated inside the latter.

4. The installation ~~has means for controlling~~ ^{is arranged for computer control of} by computer, all of the subassemblies making ^{it} possible to bring about the increase in speed of the production line automatically.

The invention also relates to a method for using such an installation, which method is characterised ~~in that~~ ^{by the following features.}

10 a) ^{It is} During the start-up phase, the temperature of the air inside each cooling zone decreases from one zone to the next, ~~it being possible for the speed of the traversing air in each zone to be adjusted and to be between 0.5 m/second and 3 m/second in each of the said zones.~~ ^{with} the drawing slot being maintained in the separated position.

b) The production speed is then increased progressively. The parameters of the zone for cooling and heating up the filaments ^{may be} being modified ~~in order~~ to:

- 20 x increase the air speed in the first zone, the temperature remaining unchanged;
- x increase the temperature in the second zone to bring it to the level of that of the first zone and increase the air speed in this zone;
- 25 x increase the air temperature in the third zone and increase the air speed in this zone; and
- x simultaneously, the width of the drawing slot is progressively reduced to attain a nominal operating value, ^{with} the pressure of the drawing air being progressively increased.

30 It should be noted that in the method according to the invention, the air temperature inside each cooling zone is generally in a range extending from 5°C to 60°C.

35 Brief description of the Drawings

The invention and the advantages which result therefrom will be better understood ~~thanks~~ to the following

with reference

Fig. exemplary embodiment, which is given by way of guidance but without limitation, and which is illustrated by the attached diagrams, in which:

X Figure 1 is a general view of an installation designed
5 in accordance with the invention;

X Figure 2 is a schematic detail view of the assembly for cooling, or more precisely controlling, the temperature of the filaments before introduction into the actual drawing slot; and *elevational*

10 X Figure 3 is a schematic *elevational* view showing the general structure of a drawing slot.

Detailed Description of the Drawings
Way of carrying out the invention

Referring to the attached Figure 1, the installation
15 according to the invention is ~~thus~~ composed essentially of at least one extruder ¹ ~~designated by the general reference (1)~~ which feeds synthetic polymer, such as polyamide, polyethylene, polyester, etc., to a spinneret (2) for the formation of a curtain of filaments (3).

20

From a practical point of view, by way of guidance, the spinneret may consist of a perforated plate containing 5000 holes, for example of 0.5 mm diameter, per metre of width. These holes are distributed over a plurality of
25 parallel rows, for example over eighteen rows, and over a width at the spinneret outlet of 140 mm.

At the outlet of this spinneret is arranged the cooling assembly (4) for adjusting the temperature of the
30 filaments depending on the polymer and which, according to the invention, is composed of three successive zones 4a, 4b and 4c. ~~(4a, 4b, 4c) for subjecting~~ the curtain of filaments (3) to with traversing air flows, the speed and temperature of which may be adjusted.

35

For example,
By way of guidance, the length of ~~this~~ ^{the} cooling zone is of the order of ~~1200~~ ¹²⁰⁰ mm and the temperature and speed of

The zones are arranged to contact

the air flows

each of the zones decreases from the first zone (4a) to the third zone (4c).

The temperature of the air in this zone will generally be between 15 and 60°C, the speed of the traversing air ~~for its part~~ being between 0.5 m/s and 3 m/s.

Downstream of this ^{The drawing assembly 5} cooling zone is arranged the actual drawing assembly (5), which is in the form of a closed enclosure having a slot (6) into which air is injected under a pressure of 0.5 to 1.5 bar.

Generally speaking, such a drawing system may be designed in a manner similar to the teachings of FR 1 582 147 or GB 932 482 (Figure 3), with which it is possible to bring about the suction of the curtain of filaments and its entrainment by high-speed air streams enabling drawing to be performed.

As can be seen from Figure 3, in which ^{the} such a drawing assembly (5) is represented schematically, the latter is composed essentially of an actual drawing slot (10). The air ~~coming~~ ^{is} from a collector (11) being introduced into ~~this~~ ^{the} chamber (10) through a distributor (12) and an accelerating chamber (13).

^{by adjustment device 10a}

Such a suction/drawing assembly is, however, preferably designed so that the width (F) of the slot (10) can be modified during the operation of the installation, which makes it possible on the one hand to adjust the flow rate of the air streams and, consequently, the fineness of the count which it is desired to achieve and on the other hand facilitates the start-up operation as will be seen hereinbelow.

35

In general, for a production of filaments having a count of between 1.5 dtx and 3 dtx, the width (F) of the

slot will be between 3 mm and 10 mm, it being possible to increase this slot gap to 25 mm during the start-up phase.

The assembly 6 causes
 5 At the outlet of the drawing assembly (5), the bundle of filaments (3) is projected onto the receiving belt (7), not directly as ~~emerges from~~ ^{disclosed in} FR 2,064,087 or US ^{patent} 4,064,605, but through an assembly (6), causing the air jet leaving the slot (5) to be deflected and slowed down, leading to the opening of the curtain of filaments and the distribution of
 10 these filaments over the receiving belt (7).

Such an assembly may, for example, be in the form of a slot with divergent walls.

15 Furthermore, to intensify the break-up of the curtain of filaments and the random distribution over the receiving surface, these filaments may be electrostatically charged by means of a system of the "corona" type which is associated with the distributing element (6), in a manner
 20 similar to the teachings of British patent 932 482.

Where appropriate, the means for electrostatically charging the filaments may be integrated in the inlet of the divergent walls of the distributor (6).
 25

Using Exemplary embodiment

in the drawings
 On an installation of the type illustrated by the attached figures, a nonwoven web consisting of continuous filaments is produced from polypropylene, in the present
 30 case 38 MSR. The polymer is melted in an extruder with five melting zones and at the outlet of the extruder, it is filtered on a filter composed of stainless steel mesh before being introduced into the actual spinneret (2).

35 To do this, the machine has two spinnerets (4) 2 arranged in series, each containing 5000 holes of 0.5 mm diameter per metre of width.

Furthermore, according to the invention, the cooling zone (4) and the drawing zone (5) preferably consist of a plurality of elementary modules each having a width of 50 cm.

5

On the other hand, the distributing element (6) ^{or assembly} arranged at the outlet of the drawing zone (5) has ~~for its part~~, a continuous slot extending over the entire width of the installation and having the form of a divergent nozzle, ^{the slot in the assembly} the width of which is 15 mm opposite the zone in which the filaments leave the slot (5) and 100 mm opposite the receiving belt (7).

10

The distributing assembly (6) ^{apparatus} may, where appropriate, be associated with additional means ^{for also} electrostatically charging the filaments, thus improving the break-up of the bundle and the distribution of these filaments over the receiving belt (7).

15

20 The line is started up at low production with a polymer delivery set at 0.2 g/min and per hole.

20

During this start-up phase, the following parameters are observed in the heating-up zone, by using a cooling zone (4) comprising three successive zones (4a, 4b, 4c) ^{that have} having a total length of about 1200 mm, ~~in the course of which~~ the extruded bundle of filaments (3) is subjected to a traversing air current coming from each of these zones, in the following conditions:

25

30

a zone (4a)

- air temperature: 35°C

- air speed: 1 m/second

b zone (4b)

35

- air temperature: 20°C

- air speed: 1 m/second

c zone (4c)

- air temperature: 15°C
- air speed: 0.5 m/second.

During this start-up cooling phase, the width (F) of
 5 the drawing slot ~~(5)~~¹⁰ is set at 25 mm, the pressure of the
 air injected into the ~~said~~ slot being 0.3 bar.

The drawn bundle ^{assembly} passes, at the ^{The assembly to} outlet of the drawing
 slot ~~(5)~~¹⁰ into the ~~system~~ ⁽⁶⁾ for the opening and
 10 distribution of the said bundle, which is in the form of a
 divergent nozzle, having a width at the inlet of 20 mm and
 an opening at the base ⁱⁿ of the order of 100 mm.

Throughout this start-up period, the polymer is
 15 collected on ^{the} a conveyor belt ~~(7)~~ by means of a "leader" (not shown)
 which is unrolled over the belt and which avoids the
 clogging thereof by the drops of melted polymer.

When a uniform polymer delivery is established in the
 20 spinneret, the production speed of the line is increased
 progressively.

Throughout this period of increasing speed, the
 parameters of the zone (4) for cooling and heating up the
 25 filaments are progressively modified, namely:

- X • increase in the air speed in the first zone ~~(4a)~~¹⁰
 to 1.5 metres/second, the temperature remaining
 unchanged;
- X • increase in the air temperature in the second
 30 zone ~~(4b)~~¹⁰ which is raised to 30°C, its speed
 being raised to 1.3 metres/second; and
- X • increase in the air temperature in the third zone
 (4c) to 20°C and increase in the speed which is
 raised to 1 metre/second.

35

Such a procedure makes it possible to ensure at least
 surface solidification of the extruded filaments, which do

not stick to one another as they enter the drawing slot
/5/.

10,
With regard to this drawing slot ~~5~~, throughout the
5 start-up period, its width is progressively reduced from
25 mm to 5 mm and, simultaneously, the pressure of the
drawing air is progressively increased from 0.3 to 1 bar,
approximately.

10 The temperature of the drawing air is controlled and
remains constant throughout this period.

By virtue of such a procedure, it is possible to
produce, from an installation in which the different zones
15 remain fixed relative to one another, polymers of different
nature and also to facilitate the production of filaments
having a very fine count of the order of 1.7 dtex, or even
less.

20 This is so because progressively raising the
temperature of the air used in the last two cooling zones
/4b/ and /4c/ makes it possible to increase the plasticity
of the polymer and thus facilitates the drawing thereof,
allowing greater fineness of the filaments.

25 Finally, the fact of being able to adjust, while in
operation, both the pressure of the drawing air and the
width of the drawing slot makes it possible to optimise ^z the
drawing conditions, which, of course, results in the
30 achievement of a high production combined with the
production of very fine filaments.

The structure of the filament-opening system, arranged
downstream of the drawing system and independent thereof,
35 also promotes regular and homogeneous deposition of the
filaments on the receiving surface /7/.

This is so because, with the production of filaments ⁱⁿ with very fine counts being accompanied by a high speed, of the order of 5000 m/min, of the filament at the outlet of the drawing slot, the device (6) used in the installation according to the invention makes it possible to slow down the speed of the ~~said~~ filaments and also of the air flow leaving the drawing slot, promoting their distribution over the conveyor belt ^{due} owing to the fact that it eliminates rebound phenomena liable to disrupt regular and homogeneous deposition.

All of the adjustments of the unit are performed and controlled automatically by a process computer which operates on the so-called "fuzzy logic" principle allowing a multitude of independent parameters to be taken into account.

The concrete example given above makes it possible to obtain filaments having a count of 1.7 dtex with a polymer delivery of 0.65 g/hole/minute.

The sheets obtained can weigh from 10 to 150 g/m², are very regular, and may be used for various applications such as hygiene products (nappies for babies), and products for medical or industrial use.

While such an installation makes it possible to obtain filaments with very fine counts, it is also possible of course to markedly increase the production of the line when the filament count is increased.

^{illustration,}
By way of ~~guidance~~, if in the above example, filaments having a count of 2 dtex had been produced, it would have been possible to increase the polymer delivery to 0.8 g/hole/minute.

CLAIMS

1. Installation for making a nonwoven textile web comprising:

- 5 - at least one extruder (1) for a melted organic polymer feeding a spinneret (2) for producing a curtain of filaments (3);
- a cooling zone (4) for bringing about at least surface solidification of the said extruded
- 10 filaments; *slot*
- a suction device (5) in the form of a narrow chamber of rectangular cross-section, inside which the curtain of filaments is subjected to the action of high-speed air streams causing the
- 15 said filaments to be drawn;
- means (6) for deflecting and slowing down the air flow at the outlet of the *suction* drawing slot and for distributing the filaments homogeneously over a receiving belt (7);

20 characterised in that the means for carrying out the different operational phases, namely extruding means, cooling means, filament-drawing assembly and distributing means, are separate from one another and can be independently adjusted, not only according to the

25 production to be achieved (nature of the polymers, elementary count of the filaments produced, weight per unit area of the web produced), but also during the start-up phase of the production.

30 2. Installation according to Claim 1, characterised in that the cooling zone (3) at the spinneret outlet and the filament-drawing zone (5) consist of a plurality of elementary modules placed side by side according to the production width, the filament-opening system consisting,

35 for its part, of an assembly extending over the entire width of the web produced.

3. Installation according to one of Claims 1 and 2, characterised in that the cooling at the spinneret (2) outlet is brought about by means of an assembly (4) having a plurality of successive zones (4a,4b,4c) for subjecting
5 the curtain of filaments to a transverse air current, the speed and temperature of which may be adjusted independently in each of the zones.

4. Installation according to one of Claims 1 to 3,
10 characterised in that the filament-drawing device (5) has a suction slot (F), the width of which may be adjusted automatically according to the production of the machine.

5. Installation according to one of Claims 1 to 4,
15 characterised in that the filament-opening system (6), which is spaced from the outlet of the drawing system, consists of an assembly which laterally deflects the air flow, reducing the speed thereof and that of the filaments, and facilitating the uniform deposition on the conveyor (7)
20 by eliminating any rebound at the moment of this deposition.

6. Installation according to Claim 5, characterised in that the filament-opening system (6) is associated with an
25 assembly which electrostatically charges the said filaments before deposition on the receiving belt.

7. Installation according to one of Claims 1 to 6, characterised in that it has means for controlling, by
30 computer, all of the subassemblies making it possible to bring about the increase in speed of the production line automatically.

8. Method for using an installation according to one
35 of Claims 1 to 7, characterised in that:

- during the start-up phase, the temperature of the air inside each cooling zone (4a,4b,4c) decreases from one

zone to the next, it being possible for the speed of the traversing air in each zone to be adjusted and to be between 0.5 m/second and 3 m/second in each of the said zones, the drawing slot being maintained in the separated position,

- the production speed is then increased progressively, the parameters of the zone (4) for cooling and heating up the filaments being modified in order to:
 - . increase the air speed in the first zone (4a), the temperature remaining unchanged,
 - . increase the temperature in the second zone (4b) to bring it to the level of that of the first zone and increase the air speed in this zone,
 - . increase the air temperature in the third zone (4c) and increase the air speed in this zone;
- simultaneously, the width of the drawing slot is progressively reduced to attain a nominal operating value, the pressure of the drawing air being progressively increased.



Abstract of The Descham

INSTALLATION FOR MAKING A NONWOVEN TEXTILE WEB AND METHOD
FOR USING SUCH AN INSTALLATION

for making a spun-bond web compuser

The ~~invention concerns an~~ installation ~~comprising~~ at least an extruder for melted organic polymer feeding a die for producing a curtain of filaments; a cooling zone for providing at least surface solidification of ~~said~~ ^{the} extruded filaments; a suction device in the form of a narrow chamber with rectangular cross-section, wherein the curtain of filaments is subjected to the action of high speed air streams causing the filaments to be drawn; ~~means~~ ^{a distributing device} for deflecting and slowing down the air flow at the outlet of the drawing slot and for distributing the filaments homogeneously on a receiving belt. The ~~invention is~~ ^{installation provides} characterised in that the ~~means for producing the~~ ^{or, means} different operational phases, namely the extruding ~~means~~, the cooling, ~~means~~ the filament drawing assembly and the distributing ~~means~~ ^{or device}, are separate from one another and can be individually adjusted, not only based on the production to be obtained (type of polymers, elementary yarn count of filaments produced, weight per unit area of the web produced), but also at the beginning of production.